



KERATILE, S.L.U.
Pol. Ind. Casablanca. Calle del Ferrocarril, 4.
12593 Moncofar, Castellon, Spain.
www.keratitle.es

MODELO / MODEL		YORKSHIRE MT		
FOTO / PICTURE (ORIENTATIVA/GUIDANCE)				
FORMATO / SIZE		20X20 cms (10mm espesor / thickness)		
GRUPO / GROUP		Bla		
TIPO / TYPE		PORCELANICO ESMALTADO / Glazed Porcelain Tile		
DESCRIPCION DEL TEST / TEST DESCRIPTION		VALOR DEL TEST / TEST VALUE	KERATILE	NORMA / STANDARD
ABSORCIÓN DE AGUA / WATER ABSORPTION		AA < 0,5%	Cumple / Passed	UNE-EN-ISO 10545-3
FUERZA DE ROTURA / BREAKING STRENGTH		> 1300 N	Cumple / Passed	UNE-EN-ISO 10545-4
RESISTENCIA A LA FLEXIÓN / RESISTANCE OF FLEXION		> 35 N/mm2	Cumple / Passed	UNE-EN-ISO 10545-4
ABRASION SUPERFICIAL / SURFACE ABRASION		Clase / Class	PEI IV	UNE-EN-ISO 10545-7
RESISTENCIA AL CUARTEO / CRACKING RESISTANCE		Requerido / Requested	Cumple / Passed	UNE-EN-ISO 10545-11
RESISTENCIA A LA HELADA / FROST RESISTANCE		Requerido / Requested	Cumple / Passed	UNE-EN-ISO 10545-12
RESISTENCIA QUIMICA / CHEMICAL RESISTANCE	(PRODUCTOS DOMESTICOS Y DE PISCINA / Domestic & Swimming Pool Products)	Mínimo / Minimum GB	Cumple / Passed	UNE-EN-ISO 10545-13
RESISTENCIA A LOS ACIDOS / ACID RESISTANCE		GHA	Cumple / Passed	UNE-EN-ISO 10545-13
RESISTENCIA A LAS BASES / ALKALINE RESISTANCE		GHA	Cumple / Passed	UNE-EN-ISO 10545-13
RESISTENCIA A LAS MANCHAS / RESISTANCE TO STAINS		Mínimo / Minimum Class 3	Cumple / Passed	UNE-EN-ISO 10545-14
RESISTENCIA AL DESLIZAMIENTO / SLIP RESISTANCE		Metodo Disponible / Available Method	Class 1	UNE-ENV 12633:2003
RESISTENCIA AL RAYADO / HARDNESS (MOHS)		Mínimo / Minimum 3	Cumple / Passed	EN 101

KERATILE S.L.U.
CIF B-12943336
Calle del Ferrocarril, 4
12593 Moncofar (Castellón) Spain
Tel. +34 964 584 069 - Fax +34 964 584 070